ROLE OF Mn(TPP)Cl IN THE EPOXIDATION WITH SINGLET OXYGEN

D. M. Boghaei and G. Zarei

Department of Chemistry, Sharif University of Technology, Tehran, Islamic Republic of Iran

Abstract

Mn(TPP)Cl catalyzes cooxidation of olefin in the singlet oxygenation of sulfid. Mn(TPP)Cl is able to transfer an oxygen atom from a peroxidic intermediate generated in singlet oxygenation of sulfide to a metal ion affording metal oxo species which is responsible for epoxidation. This system leads to alkenes epoxidation such as styrene and cyclooctene. Epoxidation of cyclohexene produces cyclohexenol, cyclohexenone and cyclohexene oxide.

Introduction

The photoxygenation of sulfides is responsible for the loss of activity of several important enzymes which are damaged in photodynamic action [1]. Much attention has been devoted to the structures and reactivities of initially formed reactive intermediates such as persulfoxide, diradical and thiadioxirane intermediates in singlet oxygenation of sulfides [2-13]. To our knowledge, no interaction between a sulfide- oxygen adduct and a metal ion is yet known. Meanwhile, a high valency iron oxo species as an active oxidant in the cytochrome p-450 mediated monoxygenases is thought to be involved in the model systems employing Manganse (III) porphyrin and chemical oxidants such as iodosylarenes [14-16], hypochlorite [17-27], tetriary amine oxides [28-38], and hydroperoxides or percarboxylic acides [31-41].

We report here an example of an oxygen atom transfer from a peroxidic intermediate generated in singlet oxygenation of sulfide to a metal ion affording metal oxo species, which is responsible for epoxidation. However, the Co-oxidation of olefin in the singlet oxygenation of sulfide catalyzed by Fe (TPEP) Cl, was reported by Wataru et. al. for the first time [42].

Keywords: Singlet oxygenation; Cooxidation; Photooxidation; Porphyrin

Experimental Section

Materials

Dichloromethane was distilled from calcium hydride, oxidation substrates (styrene, cyclohexene, ciscyclooctene, diethyl sulfide) were puchased from Merk Chemical Co.

All substrates were passed through a short column with activity I neutral alumina just prior to use to remove trace oxide contaminates and in the case of styrene to remove inhibitor, H₂ TPP, Mn (TPP) Cl were prepared by published methods [44-4].

Instrumentation

Oxidation products were analyzed on a Perkin Elmer model 8700 GC. Dodecane was used as the internal standard for calculating yields. Product identification was performed by GC-mass spectral analysis.

Photochemical Reactions

The light source was two 500-w tungsten-halogen lamps. Irradiation was carried out in a pyrex tube in an ice-water bath while oxygen was passed through.

Results and Discussion

In a typical experiment, a dichloromethane solution of diethyl sulfide ($8.3 \times 10^{-2} \,\mathrm{M}$) and cyclohexene (2.3M)

Scheme I

was photoirradiated at 20°C for 8 hours with tetraphenylporphine (TPP, $5.8 \times 10^{4} \, \text{M}$) as a sensitizer under an oxygen flow by employing a small amount of (tetraphenylporphinato) Manganes (III) chloride (MnTPP) Cl) as a catalyst. The resulting mixture was subjected to analytical GLC and GC-MS (Table 1). The products were cyclohexene oxide, cyclohexenol, cyclohexenone, diethyl sulfone and diethyl sulfoxide.

Nitrogen Bases effected as cocatalysts, as mentioned above (Table 1), in the presence of imidazole, the yields of products do not increase. We propose that this effect was due to stabilization persulfoxide intermediate generated in singlet oxygenation of sulfide by hydrogen bonding with imidazole. Its roles as an axial Mn ligand and as a base catalyst are not significant in the formation of Mn v =O intermediate. Very similar results were also obtained with cis-cyclooctene and styrene. Since less nucleophilic olefins such as styrene were scarcely (Table 1), the active oxidizing reagent in the epoxidation reaction seems to have an electronic nature. We expect that , like the Mn (porphyrin) / H_2 O_2 system [36], the capacity of the Mn catalyst to transfer an oxygen atom to the double bond increased in the following order:

TPP, TMP < TFPP < TDCPP.

'Table 1. Cooxidation of olefin in the potoxidation of Diethyl sulfide in the presence of Mn (TPP) Cl

		■ 数 2 min pr				
time	olefin :Sulfide:porphyrin	olefin	product	yield,%	Et ₂ S* conv, %	catalys ^b turnover
8h	4603: 162: 1	cyclohexenone	cyclohexene oxide cyclohexenol cyclohexenone	0. 32 14 18	55	0.3 11 15
8h	250: 130: 1	cyclohexene	cyclohexene oxide cyclohexenol cyclohexenone	0.5 37 9	7.5	0.4 30 7
8h	1250: 130: 1; Imidazol: Mn (TPP) 1: 1	cyclohexene	cyclohexene oxide cyclohexenol cyclohexenone	0.5 34 11	14.5	0.4 28 9
8h	1338: 127: 1	cis-cyclooctene	 .::::			
12h	285: 11: 1	cis-cyclooctene	cyclooctene oxide	15	28	17
12h	298: 11: 1	styrene	styrene oxide	0.9	39	0.9

^{*}In each case, Et, SO and Et, SO, were also obtained.

Epoxide produced / porphyrin used.

Consequently the primary persulfoxide intermediate is likely to trasfer an outer oxygen atom to Mn(TPP) to afford Mn^v =O (TPP)⁺, which can oxidize olefin and sulfide to epoxide and sulfoxide (Scheme 1).

References

- Sysak., P. K, Foote, C. S and Xhing, T. Y. Photobiol., 26, 19, (1977).
- Adam, W, Haas, W.and Sicker, G. J. Am. Chem. Soc., 106, 5020-5022, (1984).
- Kacher, M. L. and Foote, C. S., photo. *Photobiol.*, 29, 765, (1979).
- Jayathirtha Rao, V. and Ramamurthy, V. J. Org. Chem., 49, 615-621, (1984).
- Akasaka, T., Yabe, A. Ando, W. J. Am. Chem. Soc., 109, 8085-8087, (1987).
- 6. Jensen, F. and Foote, C. S. Ibid., 109, 1478-1485, (1987).
- Akasaka, T., Kako, M. and Sonobe, H. *Ibid.*, 110, 494-496, (1988).
- Orfanopoulos, M. and Foote, C. S. Ibid., 110, 6583-6584, (1988).
- 9. Jensen. F, and Foote, C. S. Ibid., 110, 2368-2375, (1988).
- Clennan, E. L. and Xiangning, Chen. *Ibid.*, 11, 5787-5792, (1989).
- Clennan, E. L. and Xiangning, Chen. Ibid., 11, 8212-8218, (1989).
- Clennan, E. L and Kang Young *Ibid.*, 112, 4044-4046, (1990).
- Akasaka, T., Sakarai, A, and Ando, W. *Ibid.*, 113, 2696-2701, (1991).
- Schardt, B. C., Hollander , F. J. and Hill, C. L, *Ibid.*, 104, 3964-3972, (1982)
- Birchall, T. Smegal, J. A, and Hill, C. L., *Inorg. Chem.*, 23, 1910-1913, (1984).
- Lamamoto, Y., Assis, M.D, Ciffi, K. J., Prado, C.M.C Prellwitz, B. Z., Meraes, M., Nascimento, O. R., and Sacco, H. C1 J., Mol. Catafchem, 116, 365-374, (1997).
- Bortolini, O, and Meunier, B. J. Chem. Soc., Chem. Commun. 22, 1364-1366, (1983).
- Montanari . F., Penso, M., Quici, S., and Vigano, P.J. Org. Chem. 50, 4888-4893, (1985).
- Collman, J. P., Brauman, J. I., Meuner, B., Hayashi, T., Lodadak, T. and Raybnck . S. A. J. Am . Chem . Soc. 107, 2000-2005, (1985) .
- Collman, J.P., Kodadek, T. and Brauman, J. I. *Ibid.*, 108, 2588-2594, (1986).
- Suslick, K. S. and Cook, B. R. J., Chem Soc. Chem. Commun., 3, 200-202, (1987).
- Razenberg, J. A. S., Nolte, F. J. M and Drenth, W. J., I bid.
 4, 277-279, (1986).

- Notle, R. J. M., Razenberg, J. A. S. and Schuurman, R., J. Am. Chem. Soc., 108, 2751-2752, (1986).
- Montanari, F., Banfi, S and Quici, S., Pure Appl. Chem., 61 (9), 1631-1636, (1989).
- Anelli, P. L., Banfi, S., Legramandi., F., Montanari, F., Pozzie, G. and Quici, S. J., Chem., Soc., Perkin Trans. 1,12, 1345-57, (1993).
- Banfi, S., Mnfredi, A., Montanari, F., Pozzi, G. and Quici S. J., Mol. Catal. Chem., 113, 77-86, (1996).
- 27. Chilavettol, L. B., Gugliemetti, G., Querci, C and Ricci, M. *Lett*, *Tetrah*, 37, 1091-1094, (1996).
- Brown, R. B. Williamson, Jr. M. M. and Hill, C. L., *Inorg. Chem.*, 26, 1602-1608, (1987).
- Mohajer, D. and Tangestaninejad, S. Tetrah., Lett, 35, 945-948, (1994).
- Campestrini, S., Difuria, F., Ghiotti, P. and Novello, F., J., Mol. Catal. Chem., 109, 133-139, (1996).
- 31. Lung-Chi, Yuan and Bruice, T. C., *Inorg. Chem.*, 24, 985-987, (1985).
- 32. Groves, J. T, and Watanabe, Y., *Ibid.*, 25. 4808-4810, (1986).
- 33. Lung -chi, Yan and Bruice, T. C., J. Am. chem., Soc., 108, 1643-1650, (1986).
- Balasubramanian, P. N., Sinha, A. and Bruice, T. C. J., Am. Chem. Soc., 109, 1456-1462, (1987).
- Groves, J. T. and Stern, M. K. Ibid., 109, 3812-3814, (1987).
- Battioni, P., Renaud, J. P., Bartoli, J. F. Feina-Artiles, M., Fort, M. and Mansuy, D. *Ibid.*, 110, 8462-8470, (1988).
- 37. Thellend, A, Battioni, P. and Mansuy, D. J., Chem. Soc. Chem. Commun., 9, 1035-1036, (1994).
- 38. Vilain, S., Maillard, P. and Momenteau, M. *Ibid.*, 14, 1697-1698, (1994).
- 39. Battioni, P., Lwauejko, R., Mansuy, D and Mlodnicka, T., Studies in Surface Sein. and Catal., 82, 653-658, (1994).
- Cavaleir, J. A. S. Nasscimento, Neves, M. G. P. M. S., Pinto, M. T., Silvestre, A. J. D. and Vicente, M. G. H. Tetrah. lett., 37, 1893, 1896, (1996).
- Banfi, S., Cavazzini, M., Coppa, F., Bakanova, S. V. and Kaliya, O. L. J. Chem., Soc. Perkin. Trans., 2, 1577-1583 (1997).
- 42. Akaska, T., Haranaka, M. and Ando, W. J. Am. Chem. Soc., 113, 9898-9900, (1991).
- 43. Longo, F. R. and Finarelli, J., D. J. Org. Chem., 33, 476, (1967).
- 44. Barnett, G. H., Hudson, M. F. and Smith, K. M. Tetrah Lett., 30, 2887-2888. (1973).
- 45. Fleischer, E. B., Palmer, J. M., Srivastava, T. S. and Chattergec, A. J. Am. Chem. Soc., 93, 3162-3167, (1971).